

## Description

Cast PVC film with very good weather resistance and UV stability, for high quality glass decoration. The reduced gloss of the coarse surface inhibits undesired reflection.

## Release Paper

Special polyester film, 100 micron

## Adhesive

Solvent polyacrylate, permanent

## Area of use

Developed for glass areas, to achieve a hoar-frost or freezing effect. It is specially used for the decorative designing of shop windows and glass doors. Suitable for use on cutting systems. Wet application is recommended.

## Technical Data

<b>Thickness*</b> (without paper and adhesive)	80 micron
<b>Dimensional stability</b> (FINAT TM 14)	Adhered to glass shrinkage 0,1 mm max.
<b>Temperature resistance</b>	Adhered to acrylic glass, -40° C to +90° C, no variation
<b>Resistance to cleaning agents</b>	Adhered to glass, 8h in washcalics (0,5% household cleaning agents) at room temperature and 65° C, no variation
<b>Fire behavior</b> (DIN EN 13501-1)	Flame resistant (classification B – s1,d0) on glass with a moulded density of $\geq 2250 \text{ kg/m}^3$ (indoor application)
<b>Adhesive power*</b> (FINAT TM 1, after 24h)	16 N/25 mm glass 16 N/25 mm acrylic glass
<b>Tensile strength</b> (DIN EN ISO 527)	Along: min. 9 MPa Across: min. 9 MPa
<b>Elongation at break</b> (DIN EN ISO 527)	Along: min. 40% Across: min. 40%
<b>Shelf life**</b>	2 years
<b>Application temperature</b>	> +8° C
<b>Service life by specialist application</b>	7 years
Under vertical outdoor exposure (normal climate of Central Europe)	

\* average \*\* in original packaging, at 20° C and 50% relative humidity

## Note

Surfaces to which the material will be applied must be thoroughly cleaned and free from dust, grease or any other contamination that could affect the adhesion of the material. Freshly lacquered or painted surfaces should be allowed to dry for at least three weeks and to completely cure. The compatibility of selected lacquers and paints should be tested by the user, prior to application of the material. Furthermore, the application information published by ORAFOL must be considered. The batch traceability according to ISO 9001 is possible on the basis of the roll number.

## IMPORTANT NOTICE

All ORACAL® products are subject to careful quality control throughout the manufacturing process and are warranted to be of merchantable quality and free from manufacturing defects. Published information concerning ORACAL® products is based upon research which the Company believes to be reliable although such information does not constitute a warranty. Because of the variety of uses of ORACAL® products and the continuing development of new applications, the purchaser should carefully consider the suitability and performance of the product for each intended use, and the purchaser shall assume all risks regarding such use. All specifications are subject to change without prior notice. ORACAL® is a registered trademark of ORAFOL Europe GmbH.