



# "Sol" & "Floor" Laminates Pendulum Slip Test Report

Addressee: Neil Stevenson

Report carried out on behalf of GRAFITYP UK LTD  
Grafitack House, 103 Mariner  
Lichfield Road Industrial Estate  
Tamworth  
Staffordshire  
B79 7UL

Tests conducted at Grip Potential Ltd  
Ringstead Business Centre  
1-3 Spencer Street  
Ringstead  
Northants  
NN14 4BX

Test date 23/03/10  
Report date 23/03/10

Report Reference: 180310GRAF1088  
Purchase Order: n/a

Reported results in no way imply that the flooring under test is approved or endorsed by Grip Potential Ltd. Grip Potential Ltd do not give or assume warranty or condition, express or implied, statutory or otherwise, as to condition, quality, performance, merchantability or fitness for the purpose of the test subject and all such warranties and conditions are hereby excluded save to the extent that such exclusion is absolutely prohibited by law. Grip Potential Ltd shall not be liable for any subsequent loss or damage incurred by the client as a result of information contained within this report. Results given herein refer only to areas tested by Grip Potential Ltd.



## Summary

<b>Sample</b>	<b>Slip Risk</b>	<b>Comments</b>
"Sol" laminate	High	Test results indicate a low risk of slip in dry conditions and a high risk of slip in water wet conditions.
"Floor" laminate	High	



## **Theory**

Research carried out by the Health and Safety Laboratory, in conjunction with the UK Slip Resistance Group (UKSRG), has shown that it is possible to assess the characteristics of floor surface materials needed for satisfactory slip resistance. The Health and Safety Laboratory has developed a "reliable and robust" test method that forms the basis of Grip Potential's assessment procedure.

The pendulum skid test forms the basis of the coefficient of dynamic friction measurement of a floor. A calibrated 'foot' swings from a horizontal point of release, strikes the flooring surface for a known distance, then reads the "pendulum test value" on its overswing. The rubber slider that contacts the floor is constructed of '4S' rubber (Standard Simulated Shoe Sole) and is designed to replicate the most common slipping motion experienced by pedestrians wearing shoes. A softer, more malleable, rubber (TRL rubber) may be used to simulate a barefoot or casual shoe slip. Pendulum testing is one of the few methods that models the formation of a hydrodynamic squeeze film between the floor and shoe sole, a major factor in a wet slip.

A surface roughness meter is used to measure the ability of the floor's surface to puncture the hydrodynamic squeeze film. The film forms a barrier between sole and floor and significantly reduces grip, in the same way that a car tyre aquaplanes. The minimum recommended valley to peak height for a water wet surface is 20µm. A thicker contaminant, such as motor oil, will require a much greater surface roughness in order to facilitate a sole-floor contact. For this reason it is important to take into account expected contaminants when specifying a floor surface.

A site assessment is an important component in determining the slip risk of any given floor. The HSE's pedestrian slip potential model highlights important environmental factors in a slip. Contaminating substances, frequency and methods of cleaning, types of footwear and likely pedestrian behaviour all affect the potential for a slip incident and are given due consideration.



## **Method**

### **BS 7976-2:2002 - Pendulum Testers, Method of Operation**

Coefficient of dynamic friction measurement is carried out in accordance with BS 7976 and the UKSRG Guidelines 2005. These industry standard methods of testing are essentially the same but with a slight difference between the two methods of preparation of the rubber sliders. Testing has been carried out in accordance with the UKSRG Guidelines 2005 as both the HSE and UKSRG agree that this is best practice.

A prepared standard rubber slider attached to a weighted 'shoe' is allowed to swing from a horizontal point of release. The slider is mounted on a spring loaded bracket and makes contact with the floor for a known distance. The height to which the shoe travels after contacting the floor gives a reading of the Pendulum Test Value (PTV, formally known as SRV Slip Resistance Value). The dynamic coefficient of friction of a test surface has a direct and measurable effect on the PTV reading obtained.

Test surfaces are subject to eight measurements of the PTV with the first three being discounted from calculations of the mean. Tests are carried out in the principal direction, at 45° to the principal direction and at 90° to the principal direction. Each direction is tested under both wet and dry conditions, totalling 48 measurements. A mean value is generated for wet and dry tests based on the performance in different directions. A slip potential classification can then be applied using the following table from the UKSRG Guidelines.

<b>PTV</b>	<b>Slip Potential</b>
<25	High
25-35	Moderate
>35	Low

Table 1. Slip Potential classifications from Pendulum Test Values

### **Surface Roughness Measurement (Rz)**

Surface roughness, in particular the Rz value, describes the ability of a floor to puncture the hydrodynamic squeeze film. It is also a valuable tool to assess the wear level as over time traffic will smooth a floor surface, changing its slip risk potential.

Grip Potential use a Surtronic Duo surface roughness meter for assessment. The meter moves a stylus along the test surface, measuring the floor profile's average vertical peak to valley distance in microns. A test site will be measured ten times using this method, with tests carried out in random directions in an area local to the pendulum test. This is in line with UKSRG guidelines.

Surface roughness can be used to give a general indication of the slip risk potential of a floor, though it is by no means a comprehensive test. Grip Potential use surface roughness measurements married to pendulum results to enable accurate ongoing monitoring of the surface. The UKSRG published the data shown in the table below to use in conjunction with pendulum testing.

<b>Rz (µm)</b>	<b>Slip Potential</b>
<10	High
10-20	Moderate
>20	Low

Table 2. Slip Potential classifications from surface roughness (Rz) values



## **Site Assessment**

A site assessment is designed to highlight factors that have an impact on slip risk potential. The Grip Potential site assessment follows the pedestrian slip risk potential model as developed by the HSE alongside guidance published by the UKSRG and CIRIA and our own expert knowledge and experience.

Information required to complete the site assessment is gathered primarily at the time and location of the test based on observations made by the test operator. Less obvious information, such as cleaning regimes or shoe control measures, is supplied by the person responsible for the site, or a representative of that person. Where information is uncertain, or an assumption is made, it is made clear that this is the case.

A Grip Potential site assessment aims to provide the client with all necessary information of the factors contributing to slip risk of the tested areas. Drawing assessment criteria from a wide range of expert sources ensures that a complete and thorough report of slip risk is produced. Knowledge of factors adversely affecting slip risk allows intelligent decision making in ongoing health and safety procedures.



## Test Equipment

### Munro Portable Skid Tester

Serial No: 0852  
 Calibrated by: BSI Product Services  
 Calibration date: 19/03/10  
 Certificate No: 4049  
 Calibration due: 19/03/11

**Notes:**

Calibration checks are carried out regularly by way of check testing on lapping film previously tested by a UKAS accredited laboratory. Further to this, check testing is conducted on site using lapping film and float glass of a known value.

### Surface Roughness (Rz) Meter Calibration Plate

Serial No: 112-2916  
 Calibrated by: GB Quality Assurance Ltd  
 Calibration date: 27/04/09  
 Certificate No: 55283  
 Calibration due: 27/04/10

**Notes:**

The Surtronic Duo surface roughness meter comes equipped with a calibration plate of known roughness. Prior to testing on site, check testing is carried out on the calibrated plate.

### 4S Rubber Sliders (Slider #96)

Batch No: 14816  
 Calibrated by: Munro Stanley London  
 Calibration date: 07/04/09  
 Certificate No: 63164  
 Disposal date: 30/03/10

**Notes:**

Sliders are prepared in line with guidance by the UKSRG. Check testing is conducted both on lapping film previously tested by a UKAS accredited laboratory and float glass. This procedure is conducted prior to a site visit and is in addition to the site check testing.

### TRRL Rubber Sliders (Slider #55)

Batch No: 14840  
 Calibrated by: Munro Stanley London  
 Calibration date: 07/04/09  
 Certificate No: 63164  
 Disposal date: 02/04/10

**Notes:**

Sliders are prepared in line with guidance by the UKSRG. Check testing is conducted both on lapping film previously tested by a UKAS accredited laboratory and float glass. This procedure is conducted prior to a site visit and is in addition to the site check testing.

### Digital Level

Serial No: 6029  
 Calibrated by: MD Calibration Services  
 Calibration date: 01/05/09  
 Certificate No: 110825  
 Calibration due: 01/05/10

**Notes:**

The digital level is used to determine the gradient of the test surface. The UKSRG give guidance on the effect a slope has on the recommended minimum PTV.

### On Site Check Test Values

	PTV				Mean	Expected
Lapping film:	63	63	64	64	64	63 ±1
Float glass:	9	9	9	8	9	5 to 10

Surface Roughness tested value: 21.5 µm  
 Surface roughness expected value: 21.5 µm

**Please note that all calibration certificates are available on request.**



## Test Results

## "Sol" laminate

Test carried out by: Ben Powers  
 Site location: Grip Potential Ltd  
 Substrate: Smooth ceramic tile

Date of test: 23/03/10  
 Flooring type: Self-adhesive laminate  
 Application: Unknown

Image 1. Test surface



### Pendulum Test Results

### Slider #96 (4S)

Direction	Condition	PTV					Mean
Principal	Dry	65	64	64	65	62	64
45°		63	64	64	64	64	64
90°		66	66	66	66	67	66
<b>Mean dry PTV: 65</b>							
Principal	Wet	21	21	21	21	21	21
45°		22	21	22	22	22	22
90°		25	26	26	26	26	26
<b>Mean wet PTV: 23</b>							

Pendulum test values indicate that slip risk potential in the dry is **Low**  
 Pendulum test values indicate that slip risk potential in the wet is **High**

**Low**  
**High**

The above results have been classified in accordance with the UKSRG Guidelines Issue 3, November 2005.

### Surface Roughness (Rz) Results

	Rz 0°	Rz 90°
	15.5	16.0
	16.6	16.6
	17.2	16.5
	15.3	11.8
	20.7	14.7
	13.0	14.1
	15.7	18.8
	16.3	17.7
	15.5	14.7
	11.7	11.8
<b>Mean</b>	<b>15.8</b>	<b>15.3</b>

Wet PTV: 23      Rz Value: 15.5

Assuming linear relationship between surface roughness in microns and pendulum test values, the following can be used **as a guide** when monitoring surface roughness of the test surface.

Rz Value (µm)	Indicative Slip Risk
≥ 24	Low
< 24	Moderate
< 17	High

Surface roughness measurements on this sample do not indicate a directional profile.



## Test Results

## "Floor" laminate

Test carried out by: Ben Powers  
 Site location: Grip Potential Ltd  
 Substrate: Smooth ceramic tile

Date of test: 23/03/10  
 Flooring type: Self-adhesive laminate  
 Application: Unknown

Image 1. Test surface



### Pendulum Test Results

### Slider #96 (4S)

Direction	Condition	PTV					Mean
Principal	Dry	55	56	56	56	56	56
45°		62	62	62	62	62	62
90°		52	54	54	54	54	54
<b>Mean dry PTV: 57</b>							
Principal	Wet	21	21	21	20	21	21
45°		19	19	19	19	19	19
90°		26	26	26	26	26	26
<b>Mean wet PTV: 22</b>							

Pendulum test values indicate that slip risk potential in the dry is **Low**  
 Pendulum test values indicate that slip risk potential in the wet is **High**

The above results have been classified in accordance with the UKSRG Guidelines Issue 3, November 2005.

### Surface Roughness (Rz) Results

	Rz 0°	Rz 90°
	23.3	34.7
	35.5	35.6
	25.8	25.8
	29.2	34.8
	25.6	40.7
	23.9	29.7
	31.0	28.3
	36.1	17.8
	15.9	27.6
	29.4	16.0
<b>Mean</b>	<b>27.6</b>	<b>29.1</b>

Wet PTV: 22      Rz Value: 28.3

Assuming linear relationship between surface roughness in microns and pendulum test values, the following can be used **as a guide** when monitoring surface roughness of the test surface.

Rz Value (µm)	Indicative Slip Risk
≥ 47	Low
< 47	Moderate
< 32	High

Surface roughness measurements on this sample do not indicate a directional profile.





**Conclusion**

**"Sol" laminate**

Test Method	Result
Pendulum (BS 7976) in dry conditions	Low Slip Risk
Pendulum (BS 7976) in water wet conditions	High Slip Risk
Current Rz reading	15.5
Estimated Rz threshold for low slip risk	24
Current risk management strategies	n/a

Table 1. Results from various assessment measures employed

In the opinion of Grip Potential Ltd, the sample under test demonstrated a low risk of slip in dry conditions and a high risk of slip in water wet conditions.

This sample is suitable for dry areas, however it poses a significant slip risk in water wet conditions. Contamination with more viscous liquids is highly likely to further increase the risk of a slip. Access should be restricted to any wet areas, including any wet cleaning processes. Anti-slip footwear should be considered for cleaning staff.

**"Floor" laminate**

Test Method	Result
Pendulum (BS 7976) in dry conditions	Low Slip Risk
Pendulum (BS 7976) in water wet conditions	High Slip Risk
Current Rz reading	28.3
Estimated Rz threshold for low slip risk	47
Current risk management strategies	n/a

Table 1. Results from various assessment measures employed

In the opinion of Grip Potential Ltd, the sample under test demonstrated a low risk of slip in dry conditions and a high risk of slip in water wet conditions.

This sample is suitable for dry areas, however it poses a significant slip risk in water wet conditions. Contamination with more viscous liquids is highly likely to further increase the risk of a slip. Access should be restricted to any wet areas, including any wet cleaning processes. Anti-slip footwear should be considered for cleaning staff.

The above assessment was carried out by Grip Potential adhering to the UKSRG, HSE and CIRIA guidelines on pedestrian slip risk assessment. The results given are accurate representations of data acquired on site and through the client. The results have been interpreted to give slip risk classifications based on parameters recommended by the UKSRG and HSE.

Signed: 

Ben Powers

23/03/10