PRODUCT DATA SHEET

issued: 12/2014

Avery Dennison ® Metallized Vinyl Films

- Avery Dennison Metallized Gold / Silver Films
- Avery Dennison Brushed Gold / Silver Films

Introduction

Avery Dennison Metallized Vinyl Films are top-coated metallized vinyl films coated with a permanent pressure-sensitive adhesive designed to give the appearance of a brushed chrome or gold material or alternatively mirror-like gold and silver film finish.

Description

Facefilm: 65 micron metallized vinyl film Adhesive: permanent, acrylic based

Backing paper: one side coated white kraft paper, 125 g/m²

Conversion

Avery Dennison Metallized Vinyl Films offers excellent cutting and weeding performance on a wide range of computer signmaking equipment in all popular sizes. Avery Dennison Metallized Vinyl Films can be thermal transfer printed, screen printed or digital printed. However, digital printing is not warranted, since the products do not permit profiling due to their nature. Settings may vary from one printer or ink system to another.

Features

- Excellent performance on flat and simply curved surfaces.
- Excellent layflatness and stability during cutting and weeding.
- Medium term durability and outdoor performance.
- Excellent dimensional stability during use and application.

Recommendations for use

Avery Dennison Metallized Vinyl Films can generally be used for lettering and decorations on flat to slightly curved surfaces.

- Vehicle graphics
- Functional lettering and numbering
- Retail signage
- General decorations



PRODUCT CHARACTERISTICS Physical properties

Avery Dennison[®] Metallized Vinyl Films

Features	Test method ¹	Results
Caliper, facefilm	ISO 534	65micron
Caliper, facefilm + adhesive	ISO 534	90 micron
Dimensional stability	FINAT FTM 14	0,25 mm max
Adhesion, initial	FINAT FTM-1, stainless steel	450 N/m
Adhesion, ultimate	FINAT FTM-1, stainless steel	540 N/m

Flammability self-extinguishing

Accelerated ageing SAE J 1960, 2000h exposure No negative impact on film

performance

Shelf life Stored at 22° C/50-55 % RH 1 year

Durability² Vertical exposure 5 years

Temperature range

Features Results

Application temperature Minimum: $+16^{\circ}$ C Temperature range -20° to $+75^{\circ}$ C

Chemical resistance

FeaturesTest method 1ResultsHumidity resistance200 hours exposureNo effect

Corrosion resistance 120 hours exposure to corrosion No contribution

Water resistance 48 hours immersion No effect

Important

Information on physical and chemical characteristics is based upon tests we believe to be reliable. The values listed herein are typical values and are not for use in specifications. They are intended only as a source of information and are given without guarantee and do not constitute a warranty. Purchasers should independently determine, prior to use, the suitability of this material to their specific use.

All technical data are subject to change

Warranty

Avery Dennison® branded materials are manufactured under careful quality control and are warranted to be free from defect in material and workmanship. Any material shown to our satisfaction to be defective at the time of sale will be replaced without charge. Our aggregate liability to the purchaser shall in no circumstances exceed the cost of the defective materials supplied. No salesman, representative or agent is authorized to give any quarantee, warranty or make any representation contrary to the foregoing

guarantee, warranty, or make any representation contrary to the foregoing.

All Avery Dennison branded materials are sold subject to the above conditions, being part of our standard conditions of sale, a copy of which is available on request.

1) Test methods

More information about our test methods can be found on our website.

2) Durability

The durability is based on middle European exposure conditions. Actual performance life will depend on substrate preparation, exposure conditions and maintenance of the marking. For instance, in the case of signs facing south; in areas of long high temperature exposure such as southern European countries; in industrially polluted areas or high altitudes, exterior performance will be decreased.

