

Prime Whiteboard Film White

Features

Prime Whiteboard Film is a high gloss polymeric PVC Film used for whiteboard application. The PVC is top coated with a low energy lacquer to ensure clean removal of the ink used in white board markers. The grey tinted adhesive system ensures greater opacity of the product.

The film should be applied at room temperature to achieve the best installation conditions. Apply on smooth surfaces. Please always check suitability of white board marker pen prior to installation.

The Prime Whiteboard Film is available at 1350mm x 50m. All materials used to produce this product are REACH compliant.

Technical & Performance Information

Film Thickness	150 microns
Adhesive Thickness	20 microns
Total Thickness	170 microns
Adhesive Type	grey tinted permanent based acrylic
Release Liner	130 gsm one side siliconised liner
Artificial weathering*	3 years
Film Tensile Strength	MD > 15 N/mm ²
Film Elongation	MD > 80%
Opacity	96% minimum
Adhesion to steel	(20 mins / 180 °) 7 N/25mm
Adhesion to steel	(24 hrs / 180 °) 18 N/25mm

* equivalent to vertical exposure in Mid-European climate

Dry wipe marker compatibility

Rank Scale

- 1 Need chemical cleaner to remove
- 2 Difficult to remove
- 3 Leaves ghosting
- 4 Good wipe off
- 5 Excellent wipe off with dry paper towel

Marker Brand	Model/MFC	<24 Hours	48 Hours	1 Week	3 Weeks BIC
BIC	1.4mm	5	5	5	5
Bruynzeel	color express 8	5	5	5	5
Edding	360 - 1.5mm	5	5	5	5
BIC	0.8mm	5	5	5	5
Harrow Darts	#3600	5	5	5	5
Staedtler	Lumocolor 2mm	5	5	5	5
Stabilo	Big point 88	5	5	5	5

Warranty

Prime Whiteboard Film warrants our material for one (1) year from date of shipment. The shelf life of our material is dependent on storage conditions. We recommend that the end user stores the material in the original boxes (out of direct sunlight) from our factory. We also recommend to store our material at 21°C with 50% relative humidity. We only warrants our products to be free from defects in workmanship or defects in iSee2 material. We will replace or credit any material deemed defective. No acceptance or responsibility for loss, damage or expense implied or otherwise shall be assumed by the seller or manufacturer. User assumes all risk and liability in connection herewith. All data values quoted above are typical and should not be used to deem the product defective, if measured values are different.