

## PRODUCT DATA SHEET

# Avery Dennison® MPI 2006 HOP Hi-Tack

issued: 12/2018

### Introduction

Avery Dennison Multi Purpose Inkjet 2006 HOP Hi-Tack is a gloss, white polymeric self-adhesive vinyl. Due to its special adhesive it is suitable for difficult to adhere to surfaces such as low surface energy substrates (eg. HDPE or PP) and matt interior painted walls.

As all of the HOP series products, it allows to cover a full range of flat and slightly curved medium term regular and over posting applications.

Avery Dennison MPI 2006 HOP Hi-Tack is highly recommended for a wide range of applications on flat and slightly curved substrates.

### Description

Film: 80 micron gloss white polymeric calendered vinyl with high opacity properties.  
Adhesive: Permanent, acrylic based; designed for low-surface energy substrates.  
Backing: StaFlat liner, 145 g/m<sup>2</sup>.

### Conversion

MPI 2006 HOP Hi-Tack is a multi-purpose vinyl, developed for use on various super wide format printers using hard solvent, eco/mild solvent, UV-curing or latex inks.

To enhance colour and to protect images against UV radiation and abrasion, it is recommended to protect Avery Dennison MPI 2006 HOP Hi-Tack using an overlamine or varnish.

For recommended combinations of DOL films and media, please refer to "Technical Bulletin 5.3. Recommended combinations of Avery Dennison® Overlaminates and Avery Denison® Digital Print Media".

### Uses

Avery Dennison MPI 2006 HOP Hi-Tack is recommended for a variety of applications to flat or slightly curved low-energy surfaces, such as:

- Vehicle graphics
- Architectural interior & exterior signs
- Promotional and point of sale advertising
- Exhibitions

### Features

- Excellent printability and handling on selected printers.
- Outstanding adhesion to low energy surfaces, a solution for PP and PE substrates.
- Prolonged outdoor durability of up to 7 years unprinted.
- High gloss, matt or lustre finishes\*.

\* when used in combination with DOL 2460 Gloss, DOL 2470 Matt or DOL 2480 Lustre overlaminates.



Inspired Brands  
Intelligent World.™

[graphics.averydennison.eu](http://graphics.averydennison.eu)

**Physical properties**

<b>Features</b>	<b>Test method<sup>1</sup></b>	<b>Results</b>
Caliper, facefilm	ISO 534	80 micron
Caliper, facefilm + adhesive	ISO 534	120 micron
Dimensional stability	FINAT FTM 14	1.0 mm max.
Adhesion, initial	FINAT FTM-1, HDPE	520 N/m
Adhesion, ultimate	FINAT FTM-1, HDPE	600 N/m
Flammability		Self-extinguishing
Shelf life	Stored at 23 <sup>0</sup> C/50-55% RH	2 years
Durability <sup>2</sup>	Vertical exposure	7 years

**Temperature range**

<b>Features</b>	<b>Results</b>
Application temperature:	≥ 10 °C
Service temperature:	-40°C to +80°

**NOTE:** Materials have to be properly dried before further processing, for example laminating, varnishing or application. The residual solvents could change the products' specific features.

For good print and converting result we recommend to let the rolls acclimatize in the print/lamination room at least 24h.before printing or converting. Too much temperature or humidity deviation between material and room climate can cause layflatness and/or printability issues.

Generally, constant material storage conditions of ideally 20°C (+/-2°C) /50% RH (+/- 5%), without too big climate deviations, will support a more robust and stable printing/converting process. For further details, please refer to TB 1.11.

**Important**

Information on physical and chemical characteristics is based upon tests we believe to be reliable. The values listed herein are typical values and are not for use in specifications. They are intended only as a source of information and are given without guarantee and do not constitute a warranty. Purchasers should independently determine, prior to use, the suitability of this material to their specific use. All technical data are subject to change. In case of any ambiguities or differences between the English and foreign versions of these Conditions, the English version shall be controlling.

**Warranty**

All Avery Dennison statements, technical information and recommendations are based on tests believed to be reliable but do not constitute a guarantee or warranty. All Avery Dennison products are sold with the understanding that purchaser has independently determined the suitability of such products for its purposes.

All Avery Dennison's products are sold subject to Avery Dennison's general terms and conditions of sale, see <http://terms.europe.averydennison.com>

**1) Test methods**

More information about our test methods can be found on our website.

**2) Durability**

The durability is based on middle European exposure conditions, for non-static applications (vehicles). Actual performance life will depend on substrate preparation, exposure conditions and maintenance of the marking. For instance, in the case of static signs facing south, west, or southwest, in areas of long high temperature exposure such as southern European countries; in industrially polluted areas or high altitudes, exterior performance will be decreased.