

### Description

Special PVC film with polymeric plasticisers for glass decoration. Its medium glossy surface inhibits undesired reflection. Available in silver and gold, as well as different structures.

### Release Paper

Double sided PE coated *RapidAir*® paper, one side siliconised, 145 g/m<sup>2</sup>

### Adhesive

Solvent polyacrylate, permanent

### Area of use

Developed for glass areas, to achieve a hoar-frost effect or an impression of etched, cut or sandblasted glass. It is specially used in the decoration of shop windows and glass doors. Suitable for use on cutting systems. The *RapidAir*® technology enables easy and quick bubble-free application, especially of large-sized graphics or decals. Entrapped air can be easily removed simply by rubbing the film. Suitable for even or slightly curved surfaces.

### Technical Data

<b>Thickness*</b> (without paper and adhesive)	80 micron
<b>Dimensional stability</b> (FINAT TM 14)	Adhered to glass, no measurable shrinkage in cross direction, in length 0,2 mm max.
<b>Temperature resistance</b>	Adhered to glass, -40° C to +90° C, no variation
<b>Resistance to cleaning agents</b>	Adhered to glass, 8h in washalcalics (0,5% household cleaning agents) at room temperature and 65° C, no variation
<b>Adhesive power*</b> (FINAT TM 1, after 24h)	18 N/25 mm glass 16 N/25 mm acrylic glass
<b>Tensile strength</b> (DIN EN ISO 527)	Along: min. 19 MPa Across: min. 19 MPa
<b>Elongation at break</b> (DIN EN ISO 527)	Along: min. 130% Across: min. 130%
<b>Shelf life**</b>	2 years
<b>Application temperature</b>	> +8° C
<b>Service life by specialist application</b> Under vertical outdoor exposure (normal climate of Central Europe)	7 years

\* average \*\* in original packaging, at 20° C and 50% relative humidity

### Note

Surfaces to which the material will be applied must be thoroughly cleaned and free from dust, grease or any other contamination that could affect the adhesion of the material. Freshly lacquered or painted surfaces should be allowed to dry for at least three weeks and to completely cure. The compatibility of selected lacquers and paints should be tested by the user, prior to application of the material. Furthermore, the application information published by ORAFOL must be considered. The batch traceability according to ISO 9001 is possible on the basis of the roll number.

### IMPORTANT NOTICE

All ORACAL® products are subject to careful quality control throughout the manufacturing process and are warranted to be of merchantable quality and free from manufacturing defects. Published information concerning ORACAL® products is based upon research which the Company believes to be reliable although such information does not constitute a warranty. Because of the variety of uses of ORACAL® products and the continuing development of new applications, the purchaser should carefully consider the suitability and performance of the product for each intended use, and the purchaser shall assume all risks regarding such use. All specifications are subject to change without prior notice. ORACAL® is a registered trademark of ORAFOL Europe GmbH