

Metamark MD5-AB

High Performance Digital Vinyl with Grey MetaScape® Adhesive



Product Description

Metamark MD5A-B features the MetaScape® adhesive system, offering faster and easier application by providing air with an exit route from under the graphic, with greater repositioning during application. This is combined with a grey pigmented solvent-based adhesive to provide increased opacity and preventing the substrate colour showing through. Metamark's high performance 70 micron white face film with its distinctive coating technology produces outstanding print performance on Solvent, Eco Solvent, UV and Latex printers. UK Manufactured.

Features & Benefits

- Carbon Neutral Product¹.
- For Solvent, Eco Solvent, Latex and UV printing.
- MetaScape® Adhesive System allowing ease of application.
- 7 year durability and MetaSure Warranty.
- MetaStream Ready™ – can be recycled in our closed loop recycling scheme.
- Printer manufacturer specified reference media.
- MD Series for best in class print quality & wide colour gamut.
- Engineered to give long term dimensional stability.

¹ This product has been carbon offset from cradle to first customer plus end of life. See website for details.

Face Film		Finishes		
Face Film	Polymeric Calendered Vinyl	Finishes Available	MD5-AB	White Gloss
Gauge (ISO 2286-3)	70 micron nominal	Roll Presentation		
Tensile Strength	47N/25mm MD / 43N/25mm TD nom.	Roll Widths	0.76m / 1.37m / 1.60m	
Elongation at break	180% MD nominal	Roll Lengths	50m / 25m	
Adhesive		Durability		
Type	MetaScape® permanent grey solvent based acrylic with air channels.	Shelf Life	2 years. (10-20°C and 50% R.H).	
Adhesion to glass 20 mins	15N/25mm nominal	External weathering	7 years (unprinted). Northern European conditions, vertical. Refer to full Metamark International durability guide.	
Adhesion to glass 24 hour	20N/25mm nominal	Fire Rating	Class B - BS EN 13501-1:2018	
Application temperature	+10°C to +60°C	Dimensional Stability	<0.3mm (48h at 70°C on aluminium)	
Service temperature	-30°C to +110°C	Chemical Resistance	Unprinted film resistant to mild acids, aliphatic solvents, salt and alkali, diesel, gasoline, paraffin, hydraulic oil, antifreeze.	
Release Liner		Regulations	REACH and RoHS Compliant.	
Print	MetaScape® print			
Weight	140 gsm nominal			
Type	Structured Layflat kraft paper with PE coating			

Printing and Handling

- Always perform a test print first. Ensure that the correct profiles and heater settings are used. Refer to www.metamark.co.uk.
- Ensure that the material has reached room temperature and a relative humidity of 50% before printing.
- Do not handle the face film, ensure free from dust and static.
- Overlamination is recommended to prevent abrasion, extends colour fastness, and also offers easier handling.
- The matched laminate for MD5-AB is MetaGuard MG-700 Series.

Application

- Allow a minimum of 24-48 hours for the solvents to dry off before application of the overlaminates, or to the substrate, depending on the print and drying conditions this can often be in excess of 48 hours. Retained solvents will reduce adhesion levels.
- Not recommended for use on low energy surfaces such as polypropylene.
- Apply unstressed, in particular to curves and recesses. It is not suitable for application over rivets or complex recesses.
- Suitable for dry application only.
- The user should determine suitability of substrate.



MetaStream Ready™
Film and Liner may be recycled in our closed loop recycling scheme.



Carbon neutral
Product
ClimatePartner.com/18195-2301-1001



MetaSure® Warranty

Metamark (UK) Limited warrants to its customers that graphics produced using Metamark Media and Overlaminates will remain in good condition without excessive fading or colour degradation for the specified life time of the ink used, when correctly stored, printed and applied in accordance with procedures outlined in the technical literature. If within the specified years of normal use Metamark Media and Overlaminates becomes ineffective for its intended use, then Metamark will provide sufficient material to produce a new replacement marking, and will at its own discretion, contribute an allowance in additional material towards the costs involved in replacing the graphics. In all cases, the converter is held fully responsible for storing, processing and applying the unconverted materials in accordance with Metamark's technical specifications. Metamark (UK) Limited will not be liable for any indirect or consequential loss or damage, and will not provide any allowance against improper usage, application accident, negligence, chemical damage or improper repair. The above data is given in good faith to provide an indication of the performance of the product. Purchasers should consider the suitability of each product for its intended use and the purchaser assumes all risks in connection with such use. Seller shall not be liable for damages in excess of the purchase price of the product nor for incidental nor consequential loss.

Metamark (UK) Limited

- Luneside • New Quay Road • Lancaster • LA1 5QP • Tel +44 (0)1524 387140
- Metamark House • Genesis Business Park • Albert Drive • Woking • GU21 5RW • Tel +44 (0)1483 571111

sales@metamark.co.uk
www.metamark.co.uk